



M42-32 Alkyd Deck Paint

Features: Formulated with alkyd resin, colored pigments, driers, and organic solvents. The paint film has good adhesion, is tough, glossy, full, and bright, with color retention and weather resistance. It is easy to apply.

Application: Used as an anti-abrasion coating on metal and wooden surfaces of ship decks or docks.

Basic Parameters:

- Color: Various colors, such as military green
- Finish: Glossy
- Volume Solid Content: 46%
- Density: 1.25g/ml
- Mixing Ratio: —
- Wet Film Thickness: 87 μm
- Dry Film Thickness: 40 μm
- Theoretical Coverage Rate: 11.5m²/L, 9.2m²/kg (based on a dry film thickness of 40 μm)
- Actual Coverage Rate: 6.1m²/L, 4.9m²/kg
- Flash Point: 35°C
- Surface Drying Time: 60 minutes
- Hard Drying Time: No more than 24 hours

Application

Methods: High-pressure airless spraying, rolling, brushing

Pot Life: —

Thinner: • Alkyd Thinner X-6

Recoating Interval: 24 hours

Previous
Coating
Types:

Phenolic, alkyd, epoxy ester anti-corrosion primers.

Surface Treatment:

Apply only after the previous coat is completely dry.

Packaging
Specifications:

20kg/barrel