



### M43-31 Alkyd Hull Paint

**Features:** Made from long oil alkyd resin, anti-corrosion pigments, driers, additives, and organic solvents. The paint film is bright, full, and vivid in color. It has good adhesion, flexibility, weather resistance, and protective properties, with good application performance.

**Application:** Used for decorative and protective coatings on the hull above the waterline, superstructures, and other steel structures.

#### Basic Parameters:

- Color: Various colors, such as medium gray
- Finish: Glossy
- Volume Solid Content: 46%
- Density: 1.25g/ml
- Mixing Ratio: —
- Wet Film Thickness: 87  $\mu\text{m}$
- Dry Film Thickness: 40  $\mu\text{m}$
- Theoretical Coverage Rate: 11.5 $\text{m}^2/\text{L}$ , 9.2 $\text{m}^2/\text{kg}$  (based on a dry film thickness of 40  $\mu\text{m}$ )
- Actual Coverage Rate: 6.1 $\text{m}^2/\text{L}$ , 4.9 $\text{m}^2/\text{kg}$
- Flash Point: 35°C
- Surface Drying Time: 60 minutes
- Hard Drying Time: No more than 24 hours

#### Application

**Methods:** High-pressure airless spraying, rolling, brushing

**Pot Life:** —

**Thinner:** • Alkyd Thinner X-6

**Recoating Interval:** 24 hours

Previous  
Coating  
Types:

Phenolic, alkyd, epoxy alkyd anti-corrosion paints.

Surface Treatment:

The primer and previous coats must be fully dried before applying this paint.

Packaging  
Specifications:

20kg/barrel