



### M42-31 alkyd waterline paint

**Features:** Made from alkyd resin, hard resin, anti-corrosion pigments, fillers, driers, and organic solvents. The paint film is tough, wear-resistant, and has good adhesion with certain water resistance.

**Application:** Used as an anti-abrasion coating on ship decks or metal and wooden surfaces of docks.

### Basic Parameters:

- Color: Various colors, such as maroon
- Finish: Glossy
- Volume Solid Content: 46%
- Density: 1.25g/ml
- Mixing Ratio: —
- Wet Film Thickness: 87  $\mu\text{m}$
- Dry Film Thickness: 40  $\mu\text{m}$
- Theoretical Coverage Rate: 11.5 $\text{m}^2/\text{L}$ , 9.2 $\text{m}^2/\text{kg}$  (based on a dry film thickness of 40  $\mu\text{m}$ )
- Actual Coverage Rate: 6.1 $\text{m}^2/\text{L}$ , 4.9 $\text{m}^2/\text{kg}$
- Flash Point: 35 $^{\circ}\text{C}$
- Surface Drying Time: 60 minutes
- Hard Drying Time: No more than 24 hours

### Application

**Methods:** High-pressure airless spraying, rolling, brushing

**Pot Life:** —

**Thinner:** • Alkyd Thinner X-6

**Recoating Interval:** 24 hours

Previous  
Coating  
Types:

Red iron oxide alkyd anti-corrosion primer.

Surface Treatment:

Apply only after the previous coat is completely dry

Packaging  
Specifications:

20kg/barrel